

FLEXIBLE MAGNETIC MATERIALS | PRODUCT DATA SHEET

ISO 9001 and ISO 14001 Certified
Version 1.0

PRODUCT DESCRIPTION: FERRO FILM WITH WHITE PET

CONSTRUCTION:

TOTAL THICKNESS: 0.18mm (+/-0.02mm)

- White PET 0.1mm
- Magnetic Receptive Layer 0.08mm

STANDARD WIDTH: 1070mm, 1270mm, 1370mm (+3mm/-0)

STANDARD LENGTH: 50M (+0.5M/-0)

MAGNETIC RECEPTIVENESS:

³ 3.5 g/cm²

The magnetic receptiveness is tested on Bakker Magnetics flexible magnetic sheet of 0.75mm thickness (magnetic pull 42g/cm²).

Printability:

Large Format Digital Printer: Eco-solvent inks	Yes
Large Format Digital Printer: Solvent-based inks	Yes
Large Format Digital Printer: UV inks	Yes*

* Can be used for temperatures up to 70 degrees C.

Notes:

Users should do preliminary tests to confirm printability before production. Printing problems may occur on certain machines due to ink problems or other technical problems not to our knowledge.

IMPORTANT NOTICE

Published information concerning Bakker Magnetics products is based upon research and information which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of Bakker Magnetics products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to change without prior notice. Bakker Magnetics 2015.